

## Technical Note:

# COLD EXPANSION FITTINGS

### Use with Pipe & Tubing made from Kafrit NA Cross-linked Polyethylene

Cold expansion fitting techniques have been successfully used with Kafrit NA cross-linked polyethylene for more than a decade in Europe. The most critical aspect of this technique is to ensure that the expansion of the pipe or tubing is uniform around the entire circumference of the pipe or tubing. To ensure the most uniform expansion and best quality connection, the following steps should be taken:

- Expand the pipe or tube at ambient temperatures greater than 5°C (41°F);
- Expand the pipe or tubing as slowly as possible;
- Ensure that the pipe or tubing used has uniform wall thickness before attempting to use the pipe or tubing with cold expansion fittings.

Special care should be taken when using cold expansion fittings with radiant heating tubing or pipe which has an oxygen barrier layer bonded to it. Depending on the oxygen barrier (EVOH) and adhesive that is used to bond it to the cross-linked polyethylene, problems may be observed. Check the integrity of the barrier layer and carefully check for leaks when making cold expansion connections on heating pipe or tubing.

The information contained in this document represents our best available knowledge and experience at the time of this document's last revision. This document by itself makes no warranties and puts Kafrit NA Ltd. under no obligations with regard to the products described above. Existing third party patent rights must be observed in the use of the described product.

Kafrit NA Ltd, a member of the Kafrit Group, is certified to ISO 9001:2015, ISO 14001:2015 & OHSAS 18001:2007.